

SPHERIGLASS



Potters Industries Inc.
an affiliate of The PQ Corporation

SOLID GLASS SPHERES

P.O. Box 840
Valley Forge, PA 19482-0840 USA
Telephone: (610) 651-4700 ■ Fax: (610) 408-9724
Web site: www.pottersbeads.com

Spacer Application Glass Beads

Potters Industries offers a wide range of specialized glass beads, specifically designed for controlling bond line thickness. The products meet the requirements of Hughes standard HMS20-1776B and SCGMS-53004.

Composition:	Soda-lime glass
Appearance:	Colorless sphere
Specific Gravity:	2.5
Refractive Index:	1.51
Softening Point:	704°C

Available Size Information

Potters Product Code	Hughes HMS20-1776 SCGMS-53004 Type	Nominal Maximum Diameter(Inch)	*90% of Product Within DiameterRange of: (Inch)
602578	I	.0234	.0197-.0234
602579	II	.0165	.0139-.0165
602580	III	.0117	.0098-.0117
602581	IV	.0098	.0083-.0098
602582	V	.0070	.0059-.0070
602583	VI	.0049	.0041-.0049
602584	VII	.0041	.0035-.0041
602585	VIII	.0035	.0029-.0035
602586	IX	.0029	.0025-.0029
602587	X	.0025	.0021-.0025
602588	XI	.0021	.0017-.0021
602589	XII	.0017	.0015-.0017
602590	XIII	.0015	<.0015

Minimum Order: 2 pounds North America, 5 pounds (2.26 kilograms) all exports.

Freight Terms: FOB Canby, Oregon

Packaging: 1 Pound Jars, 5 Pound Cans, or 40-50 Pound Pail

These are laboratory produced items and lead time is generally three weeks. Exceptionally large orders (over 5 pounds) may be longer. Please check with Customer Service for details.

● As determined by ASTM D-1214 Sieve analysis of glass spheres.

This document is not to be construed as an offer whose acceptance binding upon Potters Industries Inc., but is merely an invitation to make an offer instigating the possible formation of a contract shown on the reverse side hereof. SPHERIGLASS® is a registered trademark of Potters Industries Inc.